

This listing of claims will replace all prior versions of claims in this Application.

Listing of Claims

Claim 1. (Currently Amended) An electrolytic copper plating solution comprising copper, water, a water-soluble chlorine compound, a brightening agent compound having the structure represented by the formula of -X-S-Y-

wherein each of X and Y independently represents an atom selected from the group consisting of a hydrogen atom, a carbon atom, a sulfur atom, and a nitrogen atom, in which X and Y may represent the same only in the case of a carbon atom, and

B1 a thiol-reactive compound chosen from peroxy acids, aliphatic aldehyde compounds, alicyclic aldehyde compounds, aliphatic ketone compounds, alicyclic ketone compounds, hydrogen peroxide and carboxylic acids; wherein the carboxylic acids are chosen from formic acid, propionic acid, butyric acid, isobutyric acid, valeric acid, isovaleric acid, oxalic acid, malonic acid, succinic acid, glutaric acid, adipic acid, acrylic acid, methacrylic acid, crotonic acid, maleic acid, fumaric acid, citraconic acid and mesaconic acid.

Claim 2. (Currently Amended) The electrolytic copper plating solution according to claim 1, wherein the compound having the structure represented by the formula of -X-S-Y-

wherein each of X and Y independently represents an atom selected from the group consisting of a hydrogen atom, a carbon atom, a sulfur atom, and a nitrogen atom, in which X and Y may represent the same only in the case of a carbon atom, is selected from the group consisting of:

- (1) $M-SO_3-(CH_2)_a-S-(CH_2)_b-SO_3-M$;
- (2) $M-SO_3-(CH_2)_a-O-CH_2-S-CH_2-O-(CH_2)_b-SO_3-M$;
- (3) $M-SO_3-(CH_2)_a-S-S-(CH_2)_b-SO_3-M$;
- (4) $M-SO_3-(CH_2)_a-O-CH_2-S-S-CH_2-O-(CH_2)_b-SO_3-M$;
- (5) $M-SO_3-(CH_2)_a-S-C(=S)-S-(CH_2)_b-SO_3-M$;
- (6) $M-SO_3-(CH_2)_a-O-CH_2-S-C(=S)-S-CH_2-O-(CH_2)_b-SO_3-M$;

(7) $A-S-(CH_2)_a-SO_3-M$; and

(8) $A-S-CH_2-O-(CH_2)_a-SO_3-M$

wherein each of a and b represents an integer in the range of 3 to 8; M represents a hydrogen or alkali metal element; and A represents one selected from the group of: a hydrogen atom; an alkyl group having 1 to 10 carbon atoms; an aryl group; a an acyclic or cyclic amine compound ~~consisting of~~ containing 1 to 6 nitrogen atoms, 1 to 20 carbon atoms, and a plurality of hydrogen atoms; and a heterocyclic compound ~~consisting of~~ containing 1 to 2 sulfur atoms, 1 to 6 nitrogen atoms, 1 to 20 carbon atoms, and a plurality of hydrogen atoms.

Claim 3. (Original) The electrolytic copper plating solution according to claim 1, wherein the electrolytic copper plating solution contains 0.1 to 100 mg/L of the compound having the structure represented by the formula of -X-S-Y-.

Claim 4. (Canceled)

Claim 5. (Previously Presented) The electrolytic copper plating solution according to claim 1, wherein the thiol-reactive compound is present in the electrolytic copper plating solution in an amount from 1.0×10^{-4} to 1.0×10^{-1} mol/L.

Claim 6. (Previously Presented) A process for electrolytic copper plating layer to a substrate comprising contacting the substrate with the electrolytic copper plating solution of claim 1 and applying an anodic current density of 0.1 to 10 A/dm².

Claim 7. (Previously Presented) The process for electrolytic copper plating of claim 6, wherein the substrate is a printed wiring board or a wafer.

Claim 8. (Original) The process for electrolytic copper plating of claim 7, wherein the substrate has a through hole or a via hole.

Claim 9. (Canceled)

Claim 10. (Currently amended) A method for controlling an electrolytic copper plating solution comprising copper, water, a water-soluble chlorine compound, a brightening agent compound having the structure represented by the formula of -X-S-Y-

wherein each of X and Y independently represents an atom selected from the group consisting of a hydrogen atom, a carbon atom, a sulfur atom, and a nitrogen atom, in which X and Y may represent the same only in the case of a carbon atom, and

a thiol-reactive compound chosen from peroxo acids, aliphatic aldehyde compounds, alicyclic aldehyde compounds, aliphatic ketone compounds, alicyclic ketone compounds, hydrogen peroxide and carboxylic acids; wherein the carboxylic acids are chosen ~~chosen~~ from formic acid, propionic acid, butyric acid, isobutyric acid, valeric acid, isovaleric acid, oxalic acid, malonic acid, succinic acid, glutaric acid, adipic acid, acrylic acid, methacrylic acid, crotonic acid, maleic acid, fumaric acid, citraconic acid and mesaconic acid,

comprising adding the thiol-reactive compound to the electrolytic copper plating solution and maintaining a concentration of a compound having $-X-S^-$ structure equal or less than 1.0 micro mol/L.

Claim 11. (Currently Amended) The method for controlling an electrolytic copper plating solution according to claim 10, wherein the compound having the structure represented by the formula of $-X-S-Y-$ wherein each of X and Y independently represents an atom selected from the group consisting of a hydrogen atom, a carbon atom, a sulfur atom, and a nitrogen atom, in which X and Y may represent the same only in the case of a carbon atom, is selected from the group consisting of:

- (1) $M-SO_3-(CH_2)_a-S-(CH_2)_b-SO_3-M$;
- (2) $M-SO_3-(CH_2)_a-O-CH_2-S-CH_2-O-(CH_2)_b-SO_3-M$;
- (3) $M-SO_3-(CH_2)_a-S-S-(CH_2)_b-SO_3-M$;
- (4) $M-SO_3-(CH_2)_a-O-CH_2-S-S-CH_2-O-(CH_2)_b-SO_3-M$;
- (5) $M-SO_3-(CH_2)_a-S-C(=S)-S-(CH_2)_b-SO_3-M$;
- (6) $M-SO_3-(CH_2)_a-O-CH_2-S-C(=S)-S-CH_2-O-(CH_2)_b-SO_3-M$;
- (7) $A-S-(CH_2)_a-SO_3-M$; and
- (8) $A-S-CH_2-O-(CH_2)_a-SO_3-M$

wherein each of a and b represents an integer in the range of 3 to 8; M represents a hydrogen or alkali metal element; A represents: ~~one selected from the group of~~ a hydrogen atom; ~~an alkyl group having 1 to 10 carbon atoms;~~ an aryl group; ~~a;~~ an acyclic or cyclic amine compound ~~consisting of~~ containing 1 to 6 nitrogen atoms, 1 to 20 carbon atoms, and a plurality of hydrogen atoms; ~~and a heterocyclic compound consisting of~~ containing 1 to 2 sulfur atoms, 1 to 6 nitrogen atoms, 1 to 20 carbon atoms, and a plurality of hydrogen atoms.

Claim 12. (Canceled)

Claim 13. (Currently Amended) The electrolytic copper plating solution according to claim 1, wherein the aliphatic aldehyde compounds are chosen from formaldehyde, glutaraldehyde, acetaldehyde, ~~propionaldehyde, malonaldehyde~~ propionaldehyde, malonaldehyde, succinaldehyde, and glyoxal.

Claim 14. (Currently Amended) The electrolytic copper plating solution according to claim 1, wherein the peroxy acids are ~~these~~ chosen from performic acid, peracetic acid, peroxypropionic acid, peroxybutanoic acid and peroxy-pentanoic acid.

Claim 15. (Currently Amended) The electrolytic copper plating solution according to claim 1, wherein the copper solution comprises copper sulfate, copper cyanide or copper pyrophosphate.

Claim 16. (Currently Amended) The process according to claim 6, wherein the aliphatic aldehyde compounds are chosen from formaldehyde, glutaraldehyde, acetaldehyde, ~~propionaldehyde, malonaldehyde~~ propionaldehyde, malonaldehyde, succinaldehyde, and glyoxal.

Claim 17. (Currently Amended) The process according to claim 6, wherein the peroxy acids are ~~these~~ chosen from performic acid, peracetic acid, peroxypropionic acid, peroxybutanoic acid and peroxy-pentanoic acid.

Claim 18. (Currently Amended) The process according to claim 6, wherein the ~~solution~~ copper comprises copper sulfate, copper cyanide or copper pyrophosphate.

Claim 19. (Currently Amended) The method according to claim 10, wherein the aliphatic aldehyde compounds are chosen from formaldehyde, glutaraldehyde, acetaldehyde,

B1
Control

propionaldehyde, malonaldehyde~~propionaldehyde, malanaldehyde~~, succinaldehyde, and
glyoxal.
